



(19)

(11) Publication number: 0.

Generated Document.

## PATENT ABSTRACTS OF JAPAN

(21) Application number: 01248497

(51) Intl. Cl.: G01N 15/08 B01D 65/10

(22) Application date: 25.09.89

<p>(30) Priority:</p> <p>(43) Date of application publication: 10.05.91</p> <p>(84) Designated contracting states:</p>	<p>(71) Applicant: FUJI PHOTO FILM CO</p> <p>(72) Inventor: TAKAGI YASUYUKI OTANI SUMIO YOKOTA MINORU</p> <p>(74) Representative:</p>
--	---

(54) COMPLETENESS  
TESTING METHOD

(57) Abstract:

**PURPOSE:** To detect a defect of the structural parts of a filter and a filter car tridge at high precision by measuring diffusion flow rate of pressure holding value at the pressure of at least two points in a range of  $\leq 90\%$  value of a bubble point of the filter.

**CONSTITUTION:** Liquid such as water which is low in solubility of gap and small in diffusion coefficient and high in surface tension  $\delta$  is utilized for test liquid. The contact angle of test liquid and a membrane is regulated to  $\theta$ . The relation of radius (r) of a defect of a filter or a cartridge and the spray pressure P of test liquid is shown in  $r=2\delta\cos\theta/P$ . Spray amount QL(ml/min) is obtained by an expression  $QL=15\pi d^4\sqrt{P/32L\eta}$  in the case of (d) ( $\mu\text{m}$ ) diameter of a defect,  $\sqrt{P}$  (bar) differential pressure, L(m) length of the defect and  $\eta$  ( $\mu\text{poise}$ ) viscosity

of spray fluid. Accordingly, completeness can be tested at the pressures for two or more points of  $\leq$  90% value of bubble, with the diffusion flow rate or pressure holding value and differential values between measurement points as an inspection standard point.

COPYRIGHT: (C)1991,JPO&Japio